

## PRODUCT DATA

Brand Name: FURNACUBED™ 70

**Description:** FURNACUBED™ 70 is a 74% alumina, non-wetting to aluminum, low cement castable that can be vibration cast, self-flow cast,

or shotcreted. This product has excellent thermal shock resistance to 2000°F. It has been used for preformed blocks in an aluminum furnace and has been shotcreted in aluminum furnace upper and lower walls. Unlike other FURNACUBED™ products, this product is recommended for use only in aluminum furnace applications. Therefore, its maximum non-metal

contact use temperature is 2500°F.

Physical properties shown are average values of samples taken under controlled conditions ASTM test methods used where applicable

Maximum Service Temperature: 2500°F (1371°C) Aluminum Furnace Non-Metal Contact 2200°F (1371°C) Aluminum Non-Wetting

Typical Water Required for Mixing (by weight):	Dry Material Required per Cubic Foot:				
Vibration Casting		Shotcrete		170 - 176 lbs	
Self Flow Casting	4.0 - 5.0%	Self Flow	. 162 - 168 lbs	162 - 168 lbs	
	Sho	Shotcrete Data		Self Flow/Pump Casting Data	
Bulk Density (pcf)				<u> </u>	
After 220°F (105°C)	157 - 161	(2.27 - 2.34 g/cm <sup>3</sup> )	158 - 168	(2.21 - 2.27 g/cm <sup>3</sup> )	
After 1500°F (815°C)	155 - 161	(2.24 - 2.30 g/cm <sup>3</sup> )	166 - 170	(2.16 - 2.23 g/cm <sup>3</sup> )	
Cold Crushing Strength (psi)					
After 220°F (105°C)	3400 - 7400	(700 - 980 kg/cm <sup>2</sup> )	3400 - 7300	(350 - 630 kg/cm <sup>2</sup> )	
After 1500°F (815°C)	3000 - 7000	(560 - 840 kg/cm <sup>2</sup> )	5500 - 10000	(210 - 490 kg/cm <sup>2</sup> )	
Modulus of Rupture (psi)					
After 220°F (105°C)	700 - 1100	(77 - 105 kg/cm <sup>2</sup> )	1100 - 2100	(49 - 77 kg/cm <sup>2</sup> )	
After 1500°F (815°C)	700 - 900	(105 - 133 kg/cm <sup>2</sup> )	1100 - 2800	(42 - 70 kg/cm <sup>2</sup> )	
Apparent Porosity (%)					
After 220°F (105°C)	13 - 20		8 - 14		
After 1500°F (815°C)	18 - 22		15 - 18		
Permanent Linear Change (%)					
After 1500°F (815°C)	-0.4 to 0.2		-0.4 to 0.2		
Typical Chemical Analysis (%) (Calcined Basis)					
Alumina (Al <sub>2</sub> O <sub>3</sub> )	74.0				
Silica (SiO <sub>2</sub> )	17.6				
Lime (CaO)	1.2				
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> )	0.9				
Titania (TiO <sub>2</sub> )	2.0				
Magnesia (MgO)	0.2				
Alkalies (Na <sub>2</sub> O+K <sub>2</sub> O)	0.2				
Other	3.9				

Standard Packaging:

55 lb bag. 72 bags per pallet. Bulk packaging available.

Brand Code: 0876

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

1/12/2017 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505