



PRODUCT DATA

Brand Name: HM 28 LI

Description: HM 28 LI is a low iron refractory gunning mix based on hard fired alumina/silica aggregate of approximately 60% mullite content and a low iron calcium aluminate binder.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 2800°F (1538°C)

Bulk Density (pcf)

After 300°F (149°C)

Gunning Data

130 (2.08 g/cm³)

Modulus of Rupture (psi)

After 300°F (149°C)

600 - 900 (42 - 63 kg/cm²)

Permanent Linear Change (%)

After 300°F (149°C)

-0.2 to -0.1

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	45.0
Silica (SiO ₂)	43.4
Iron Oxide (Fe ₂ O ₃)	1.2
Titania (TiO ₂)	2.3
Lime (CaO)	6.2
Magnesia (MgO)	0.5
Alkalis (Na ₂ O+K ₂ O)	1.2
Other	3.0

Standard Packaging: 55 lb bag. 72 bags per pallet. Bulk packaging available.

Brand Code: 3030

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

01/17/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505