



PRODUCT DATA

Brand Name:

RESCOBOND MAAX

Description: Rescobond MAAX, like Rescobond AA-22S, is a chemically bonded, erosion resistant, single component refractory material used primarily in thin lining applications to protect against severe abrasion. To prepare for use, blend Rescobond MAAX with water. Rescobond MAAX is an air setting material, and it utilizes the same binder system as Rescobond AA-22S. It can also be used to patch other refractory linings. Rescobond MAAX is an upgraded version of Rescobond AA-22S.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 2600°F (1427°C)

Typical Water Required for Mixing (by weight) :

Casting 4.8%

Bulk Density (pcf)	<u>Cast Data</u>	
After 1500°F (815°C)	168	(2.69 g/cm ³)
Cold Crushing Strength (psi)		
After 1500°F (815°C)	20500	(1435 kg/cm ²)
Modulus of Rupture (psi)		
After 1500°F (815°C)	2500	(175 kg/cm ²)
Thermal Conductivity (K Factor)	<u>BTU/ft²/hr./°F/inch</u>	<u>W/mK</u>
500°F (260°C)	15.7	2.28
1000°F (538°C)	15.4	2.23
1500°F (815°C)	15.6	2.27
Permanent Linear Change (%)		
Green to 1500°F (815°C)	-0.4 to 0.0	
Abrasion Loss (using ASTM C-704 Method)		
After 1500°F (815°C)	3 cc (max)	

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	80.0
Silica (SiO ₂)	7.0
Iron Oxide (Fe ₂ O ₃)	0.9
Lime + Magnesia (CaO+MgO)	4.7
Alkalies (Na ₂ O+K ₂ O)	0.1
Phosphorus Pentoxide (P ₂ O ₅)	4.4
Others	2.9

Standard Packaging: 55 lb bag. 72 bags per pallet. Bulk packaging available.

Brand Code: 8917

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/13/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.