



# PRODUCT DATA

**Brand Name:**

## RESCOCAST 9LI-SW

**Description:** RESCOCAST 9LI-SW combines the qualities of an insulating and a general duty castable. High strength and good protection against heat loss have made this product an ideal choice for the gunning of FCC regenerator and reactor walls. RESCOCAST 9LI-SW has been used throughout the world for this and other critical applications. RESCOCAST 9LI-SW can be installed by either casting or gunning.

Physical properties shown are average values of samples taken under controlled conditions  
ASTM test methods used where applicable

**Maximum Service Temperature: 2400°F (1316°C)**

**Typical Water Required for Mixing (by weight) :**

Cast ..... 26%  
Predampening for Gunning ..... 8.3 - 10.4%

<u>Bulk Density (pcf)</u>	<u>Casting Data</u>		<u>Gunning Data</u>	
After 1500°F (815°C)	78	(1.25 g/cm <sup>3</sup> )	90	(1.44 g/cm <sup>3</sup> )
<u>Cold Crushing Strength (psi)</u>				
After 1500°F (815°C)	1950	(137 kg/cm <sup>2</sup> )	2500	(175 kg/cm <sup>2</sup> )
<u>Thermal Conductivity (K Factor)</u>				
Mean Temperature	<u>BTU/ft<sup>2</sup>/hr./°F/inch</u>	<u>W/mK</u>	<u>BTU/ft<sup>2</sup>/hr./°F/inch</u>	<u>W/mK</u>
500°F (260°C)	3.1	0.45	3.7	0.54
1000°F (540°C)	2.6	0.38	3.2	0.46
1500°F (815°C)	2.9	0.42	3.5	0.51
<u>Permanent Linear Change (%)</u>				
Green to 1500°F (815°C)	-0.4 to 0.0		-0.4 to 0.0	
230°F (110°C) to 1500°F (815°C)	-0.3 to 0.0		-0.3 to 0.0	

### Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al <sub>2</sub> O <sub>3</sub> ) .....	31.8
Silica (SiO <sub>2</sub> ) .....	46.5
Lime (CaO) .....	12.7
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ) .....	4.3
Titania (TiO <sub>2</sub> ) .....	1.3
Magnesia (MgO) .....	1.4
Alkalies (Na <sub>2</sub> O+K <sub>2</sub> O) .....	2.0

**Standard Packaging:** 50 lb bag. 50 bags per pallet. Bulk packaging available.

Brand Code: 0340

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/22/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505