



PRODUCT DATA

RESCOLITE 23-50LI QT

Brand Name:

Description: RESCOLITE 23-50 LI QT is a low iron, lightweight castable with a nominal 50 pcf density that can be installed by casting or conventional gunning methods with reduced dust levels. This low iron lightweight castable is suitable for reducing and hydrogen atmospheres. After the initial set, the refractory can be initially heated up without following the traditional ramp-and-hold schedule. Resco's QUIKTURN schedule is recommended to be followed

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 2300°F (1260°C)

Typical Water Required for Mixing (by weight) :

Casting 55%
Predampening for Gunning 10%

	Casting Data		Gunning Data	
Bulk Density (pcf)				
After 1500°F (815°C)	51	(0.82 g/cm ³)	64	(1.03 g/cm ³)
Cold Crushing Strength (psi)				
After 1500°F (815°C)	700	(49 kg/cm ²)	1500	(105 kg/cm ²)
Thermal Conductivity (K Factor)				
Mean Temperature	<u>BTU/ft²/hr./°F/inch</u>	<u>W/mK</u>	<u>BTU/ft²/hr./°F/inch</u>	<u>W/mK</u>
500°F (260°C)	2.29	0.33	2.84	0.41
1000°F (540°C)	1.80	0.26	2.29	0.33
1500°F (815°C)	2.08	0.30	2.64	0.38
Permanent Linear Change (%)				
Green to 1500°F (815°C)	-0.6 to 0.0		-0.6 to 0.0	
230°F (110°C) to 1500°F (815°C)	-0.5 to 0.0		-0.4 to 0.0	

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	40.1
Silica (SiO ₂)	37.1
Lime (CaO)	16.8
Iron Oxide (Fe ₂ O ₃)	1.0
Titania (TiO ₂)	0.8
Magnesia (MgO)	0.3
Alkalies (Na ₂ O+K ₂ O)	2.6

Standard Packaging: 35 lb bag. 50 bags per pallet. Bulk packaging available.

Brand Code: 8980

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/24/2021 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505