



PRODUCT DATA

Brand Name: SPRAY MIX® S-506

Description: SPRAY MIX® is a 40% alumina, superduty fireclay, air-setting refractory coating mix with a service temperature limit of 3000°F. It is specially designed to lengthen the life of the refractory to which it is applied. With refractory properties similar to superduty brick, it is especially well suited for patching firebrick walls that are spalled and worn. SPRAY MIX® adheres well to the refractory surface and forms a bond with it at normal furnace operating temperatures. The surface should be carefully built up by spraying successive thin layers over top of one another. It can be used as a preventative maintenance veneer coating over new walls. It can be placed by spraying, trowelling, or hand packing to a refractory surface cleaned of loose material and dust and moistened to prevent loss of water from the coating. It adheres best when applied to a hot or warm lining.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 3000°F (1649°C)

Typical Chemical Analysis (%)
(Calcined Basis)

	Dry	Wet
Alumina (Al ₂ O ₃)	16.3	39.8
Silica (SiO ₂)	81.1	53.9
Iron Oxide (Fe ₂ O ₃)	0.8	1.6
Titania (TiO ₂)	0.8	1.6
Lime (CaO)	0.2	0.4
Magnesia (MgO)	0.2	0.2
Alkalis (Na ₂ O+K ₂ O)	0.6	2.5

Standard Packaging: 55 lb bag (Dry) 100 lb drum (Wet)

Brand Code: 1128

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/13/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.