



PRODUCT DATA

Brand Name:

VIBROCAST 60Z PC

Description: A 60% alumina, low cement castable containing zircon. This product can be installed using vibration casting, pumping, and shotcrete installation methods.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 3100°F (1700°C)

| | Pump Cast Data | |
|---|----------------|---------------------------|
| <u>Bulk Density (pcf)</u> | | |
| After 220°F (105°C) | 158 | (2.53 g/cm ³) |
| After 1500°F (815°C) | 157 | (2.51 g/cm ³) |
| <u>Cold Crushing Strength (psi)</u> | | |
| After 1500°F (815°C) | 12000 | (840 kg/cm ²) |
| <u>Modulus of Rupture (psi)</u> | | |
| After 1500°F (815°C) | 1700 | (119 kg/cm ²) |
| <u>Permanent Linear Change (%)</u> | | |
| After 1500°F (815°C) | -0.3 to -0.1 | |
| <u>Abrasion Loss (using ASTM C-704 Method)</u> | | |
| After 1500°F (815°C) | 8 cc (max) | |
| <u>Typical Chemical Analysis (%)</u> (Calcined Basis) | | |
| Alumina (Al ₂ O ₃) | 57.1 | |
| Silica (SiO ₂) | 35.2 | |
| Iron Oxide (Fe ₂ O ₃) | 0.9 | |
| Titania (TiO ₂) | 1.5 | |
| Lime (CaO) | 1.6 | |
| Zirconia (ZrO ₂) | 3.3 | |
| Alkalis (Na ₂ O+K ₂ O) | 0.2 | |

Standard Packaging: 55 lb bag. 72 bags per pallet. Bulk packaging available.

Brand Code: 1564

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

04/03/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.