

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations Issue date: 4/14/2023 Revision date: 4/14/2023 Supersedes: 10/19/2020

SECTION 1: Identification

1.1. Identification

Product form : Mixture
Product name : FurnaCubed 85
CAS-No. : Mixture
Product code : 1113

Other means of identification : Alumina-Silicate Cement Bonded Castable

1.2. Recommended use and restrictions on use

Use of the substance/mixture : Refractory Recommended use : Industrial use

1.3. Supplier

Resco Products, Inc.
One Robinson Plaza, Suite 300
6600 Steubenville Pike
Pittsburgh, PA, 15205
United States
412-494-4491

SDS@RescoProducts.com - WWW.RescoProducts.com

1.4. Emergency telephone number

Emergency number : EMERGENCY ONLY (CHEMTREC) USA & Canada 1-800-424-9300

Outside USA & Canada +1 703-741-5970

SECTION 2: Hazard(s) identification

2.1. Classification of the substance or mixture

GHS US classification

Skin corrosion/irritation Category 2

Serious eye damage/eye irritation Category 2B

Carcinogenicity Category 1A

H315

Causes skin irritation

Causes eye irritation

Causes eye irritation

May cause cancer (Inhalation)

Full text of H statements: see section 16

2.2. GHS Label elements, including precautionary statements

GHS US labeling

Hazard pictograms (GHS US)





Signal word (GHS US) : Danger

Hazard statements (GHS US) : H315 - Causes skin irritation H320 - Causes eye irritation

H350 - May cause cancer (Inhalation)

Precautionary statements (GHS US) : P280 - Wear eye protection, Dust respirator, protective gloves.

P305+P351+P338 - IF IN EYES: Rinse cautiously with water for several minutes. Remove

contact lenses, if present and easy to do. Continue rinsing. P332+P313 - If skin irritation occurs: Get medical advice/attention. P337+P313 - If eye irritation persists: Get medical advice/attention.

P260 - Do not breathe dust.

2.3. Other hazards which do not result in classification

No additional information available

2.4. Unknown acute toxicity (GHS US)

No additional information available

SECTION 3: Composition/Information on ingredients

3.1. Substances

Not applicable

3.2. Mixtures

o.z. mixtures			
Name	Product identifier	%	GHS US classification
aluminium oxide, non-fibrous	CAS-No.: 1344-28-1	50 – 75	Not classified
Calcium Aluminate Cement	CAS-No.: 65997-16-2	1 – 5	Skin Irrit. 2, H315
			Eye Irrit. 2B, H320
calcium fluoride	CAS-No.: 7789-75-5	1 – 5	Not classified
quartz	CAS-No.: 14808-60-7	0.1 - 0.5	Carc. 1A, H350

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

Name	Product identifier	%	GHS US classification
cristobalite	CAS-No.: 14464-46-1	0.1 - 0.5	Carc. 1A, H350

Full text of hazard classes and H-statements : see section 16

SECTION 4: First-aid measures

4.1. Description of first aid measures

First-aid measures general : Never give anything by mouth to an unconscious person. If you feel unwell, seek medical advice

(show the label where possible).

First-aid measures after inhalation : Allow affected person to breathe fresh air. Allow the victim to rest.

First-aid measures after skin contact : Gently wash with plenty of soap and water.

First-aid measures after eye contact : IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present

and easy to do. Continue rinsing.

First-aid measures after ingestion : Rinse mouth. Do NOT induce vomiting. Obtain emergency medical attention.

4.2. Most important symptoms and effects (acute and delayed)

Potential Adverse human health effects and : Based on available data, the classification criteria are not met.

symptoms

Symptoms/effects after inhalation : May cause cancer by inhalation. Danger of serious damage to health by prolonged exposure

through inhalation.

Symptoms/effects after skin contact : Causes skin irritation. Symptoms/effects after eye contact : Causes eye irritation.

4.3. Immediate medical attention and special treatment, if necessary

No additional information available

SECTION 5: Fire-fighting measures

5.1. Suitable (and unsuitable) extinguishing media

Suitable extinguishing media : Use extinguishing media appropriate for surrounding fire.

Unsuitable extinguishing media : In case of fire, all extinguishing media allowed.

5.2. Specific hazards arising from the chemical

Fire hazard : Not flammable.

5.3. Special protective equipment and precautions for fire-fighters

Firefighting instructions : Fight fire with normal precautions from a reasonable distance.

Protection during firefighting : Do not enter fire area without proper protective equipment, including respiratory protection.

SECTION 6: Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures

6.1.1. For non-emergency personnel

Emergency procedures : Do no

6.1.2. For emergency responders

: Do not breathe dust. Avoid contact with skin and eyes.

Protective equipment Emergency procedures Equip cleanup crew with proper protection.

Ventilate area. On land, sweep or shovel into suitable containers.

6.2. Environmental precautions

Prevent entry to sewers and public waters.

6.3. Methods and material for containment and cleaning up

Methods for cleaning up : On land, sweep or shovel into suitable containers. Minimize generation of dust.

6.4. Reference to other sections

See Heading 8. Exposure controls and personal protection.

SECTION 7: Handling and storage

7.1. Precautions for safe handling

Precautions for safe handling : Do not handle until all safety precautions have been read and understood. Avoid raising dust.

Avoid contact with skin and eyes. Do not breathe dust.

Hygiene measures : Wash hands and other exposed areas with mild soap and water before eating, drinking or

smoking and when leaving work.

7.2. Conditions for safe storage, including any incompatibilities

Storage conditions : Store this product in a dry location where it can be protected from the elements.

Incompatible products : Strong bases. Strong acids.

SECTION 8: Exposure controls/personal protection

8.1. Control parameters

4/14/2023 (Revision date) EN (English US) 2/8

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

FurnaCubed 85 (Mixture)	
No additional information available	
Calcium Aluminate Cement (65997-16-2)	
No additional information available	
cristobalite (14464-46-1)	
USA - ACGIH - Occupational Exposure Limits	
ACGIH OEL TWA	0.025 mg/m³ respirable dust
USA - OSHA - Occupational Exposure Limits	
OSHA PEL (TWA) [1]	0.05 mg/m³ respirable dust
calcium fluoride (7789-75-5)	
USA - ACGIH - Occupational Exposure Limits	
ACGIH OEL TWA	2.5 mg/m³
aluminium oxide, non-fibrous (1344-28-1)	
USA - ACGIH - Occupational Exposure Limits	
ACGIH OEL TWA	1 mg/m³ respirable dust
quartz (14808-60-7)	
USA - ACGIH - Occupational Exposure Limits	
ACGIH OEL TWA	0.025 mg/m³ (Silica-Crystalline Quartz; USA; Time-weighted average exposure limit 8 h; TLV - Adopted Value; Respirable fraction)
USA - OSHA - Occupational Exposure Limits	
Local name	Silica, crystalline quartz, respirable dust
OSHA PEL (TWA) [1]	0.05 mg/m³ respirable dust
Remark (OSHA)	(3) See Table Z-3.
8.2. Appropriate engineering controls	
Appropriate engineering controls :	Provide adequate ventilation to minimize dust concentrations.
8.3. Individual protection measures/Personal Personal protective equipment: Avoid all unnecessary exposure.	protective equipment
Hand protection:	
Wear protective gloves.	
Eye protection:	
Chemical goggles or safety glasses	

Other information:

Do not eat, drink or smoke during use.

Skin and body protection:Wear suitable protective clothing

Respiratory protection:
Wear appropriate mask

SECTION 9: Physical and chemical properties

9.1. Information on basic physical and chemical propertiesPhysical state : Solid

Appearance : Granular mixture.

Color : Gray Odor : earthy

4/14/2023 (Revision date) EN (English US) 3/8

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

Odor threshold	:	No data available
pH	:	No data available
Melting point	:	> 2000 °F
Freezing point	:	No data available
Boiling point	:	No data available
Flash point	:	No data available
Relative evaporation rate (butyl acetate=1)	:	No data available
Flammability (solid, gas)	:	Non flammable.
Vapor pressure	:	No data available
Relative vapor density at 20°C	:	No data available
Relative density	:	No data available
Solubility	:	Slightly soluble.
Partition coefficient n-octanol/water (Log Pow)	:	No data available
Auto-ignition temperature	:	No data available
Decomposition temperature	:	No data available
Viscosity, kinematic	:	Not Applicable
Viscosity, dynamic	:	No data available
Explosion limits	:	No data available
Explosive properties	:	No data available
Oxidizing properties	:	No data available

9.2. Other information

No additional information available

SECTION 10: Stability and reactivity

10.1. Reactivity

Hydraulic setting.

10.2. Chemical stability

Stable under normal conditions of use.

10.3. Possibility of hazardous reactions

Not established.

10.4. Conditions to avoid

Avoid dust formation.

10.5. Incompatible materials

Strong acids. Strong bases.

10.6. Hazardous decomposition products

No additional information available

SECTION 11: Toxicological information

11.1. Information on toxicological effects

Not classified Acute toxicity (oral) Acute toxicity (dermal) Not classified Acute toxicity (inhalation) Not classified

calcium fluoride (7789-75-5)	
LD50 oral rat	> 2000 mg/kg body weight (OECD 423: Acute Oral Toxicity – Acute Toxic Class Method, Rat, Female, Experimental value, Oral, 14 day(s))
LD50 dermal rat	> 2000 mg/kg body weight (EPA OPP 81-2, 24 h, Rat, Male / female, Experimental value, Dermal, 14 day(s))
LC50 Inhalation - Rat	> 5.07 mg/l air (OECD 403: Acute Inhalation Toxicity, 4 h, Rat, Male / female, Experimental value, Inhalation (dust), 14 day(s))
aluminium oxide, non-fibrous (1344-28-1)	
LD50 oral rat	> 15900 mg/kg body weight (Equivalent or similar to OECD 401, Rat, Male / female, Experimental value, Oral, 14 day(s))
LC50 Inhalation - Rat	> 2.3 mg/l air (Equivalent or similar to OECD 403, 4 h, Rat, Male / female, Experimental value, Inhalation (aerosol), 14 day(s))
Skin corrosion/irritation :	Causes skin irritation.

Calcium Aluminate Cement (65997-16-2)	
рН	≤ 13

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

cristobalite (14464-46-1)	
рН	6 – 7
calcium fluoride (7789-75-5)	
рН	No data available in the literature
aluminium oxide, non-fibrous (1344-28-1)	
рН	9 – 10.5 (aqueous suspension, 33 %)
quartz (14808-60-7)	
рН	6 – 7
Serious eye damage/irritation :	Causes eye irritation.
Calcium Aluminate Cement (65997-16-2)	
pH	≤ 13
cristobalite (14464-46-1)	
рН	6 – 7
calcium fluoride (7789-75-5)	
рН	No data available in the literature
aluminium oxide, non-fibrous (1344-28-1)	
рН	9 – 10.5 (aqueous suspension, 33 %)
quartz (14808-60-7)	
рН	6 – 7
Respiratory or skin sensitization :	Not classified
Germ cell mutagenicity :	Not classified
Carcinogenicity :	May cause cancer (Inhalation).
quartz (14808-60-7)	
IARC group	1 - Carcinogenic to humans
Reproductive toxicity :	Not classified
STOT-single exposure : STOT-repeated exposure :	Not classified Not classified
Aspiration hazard :	Not classified
Viscosity, kinematic :	Not Applicable
calcium fluoride (7789-75-5)	
Viscosity, kinematic	Not applicable (solid)
aluminium oxide, non-fibrous (1344-28-1)	
Viscosity, kinematic	Not applicable (solid)
Potential Adverse human health effects and :	Based on available data, the classification criteria are not met.
symptoms Symptoms/effects after inhalation :	May cause cancer by inhalation. Danger of serious damage to health by prolonged exposure
Symptoms/effects after skin contact :	through inhalation. Causes skin irritation.
Symptoms/effects after eye contact :	Causes eye irritation.
SECTION 12: Ecological information	
12.1. Toxicity	
calcium fluoride (7789-75-5)	
LC50 - Fish [1]	107.5 ppm (EPA 600/3-75/009, 96 h, Oncorhynchus mykiss, Static system, Fresh water, Readacross, Lethal)
·	

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	aluminium oxide, non-fibrous (1344-28-1)			
### Parsistence and degradability Parsistence and degradability Not established.	LC50 - Fish [1]	> 100 mg/l (96 h, Salmo trutta, Literature study)		
Persistence and degradability Persistence and degradability Mineral. Not applicable. Chemical oxygen demand (COD) Not applicable Biodegradability Persistence and degradability Not applicable Not applicable Biodegradability Persistence and degradability Biodegradability: not applicable Calcium fluoride (7789-75-5) Persistence and degradability Biodegradability: not applicable. Chemical oxygen demand (COD) Not applicable (inorganic) ThOD Not applicable (inorganic) Antiminum oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable Quartz (14808-60-7) Persistence and degradability Not applicable Biochemical oxygen demand (COD) Not applicable Biochemical oxygen demand (COD) Not applicable Chemical oxygen demand (COD) Not applicable Biochemical oxygen demand (COD) Not applicable Chemical oxygen demand (COD) Not applicable Biochemical oxygen demand (COD) Not applicable Cristobalite (14464-46-1) Biocccumulative potential Not established. Cristobalite (14464-46-1) Biocccumulative potential Not data available. Calcium fluoride (7789-75-5) BCF - Fish [1] O - 6.4 Wg (OECD 305: Bioccncentration: Flow-Through Fish Test, 4 week(s), Cyprinus capion free water, Experimental value) Biocccumulative potential No data available. 12.4. Mobility in soil Cristobalite (14464-46-1) Biocccumulative potential No data available. 12.4. Mobility in soil Cristobalite (14464-46-1)	EC50 - Crustacea [1]	> 100 mg/l (48 h, Daphnia magna, Literature study)		
Persistence and degradability Mineral. Not applicable. Cristobalite (14464-46-1) Persistence and degradability Mineral. Not applicable. Chemical oxygen demand (COD) Not applicable BOD (% of ThOD) Not applicable Calcium fluoride (7789-75-5) Persistence and degradability Biodegradability: not applicable (inorganic) ThOD Not applicable (inorganic) Inorganic) Inorganic (COD) Not applicable (inorganic) Inorgan	12.2. Persistence and degradability			
cristobalite (14464-46-1) Persistence and degradability Mineral. Not applicable. Chemical oxygen demand (COD) Not applicable BOD (% of ThOD) Not applicable BOD (% of ThOD) Not applicable Calcium fluoride (7789-75-5) Persistence and degradability Biodegradability: not applicable. Chemical oxygen demand (COD) Not applicable (inorganic) ThOD Not applicable (inorganic) aluminium oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable. Chemical oxygen demand (COD) Not applicable ThOD Not applicable quartz (14808-60-7) Persistence and degradability Not applicable Biodegradability Not applicable Chemical oxygen demand (COD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential Not data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 64 l/tg (DECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carplor Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	FurnaCubed 85 (Mixture)			
Persistence and degradability Chemical oxygen demand (COD) Not applicable DOD (% of ThOD) Not applicable DOD (% of ThOD) Not applicable DOD (% of ThOD) Not applicable Calcium fluoride (7789-75-5) Persistence and degradability Biodegradability: not applicable. Chemical oxygen demand (COD) Not applicable (inorganic) ThOD Not applicable (inorganic) Not applicable (inorganic) ThOD Not applicable (inorganic) Not applicable Chemical oxygen demand (COD) Not applicable Chemical oxygen demand (COD) Not applicable ThOD Not applicable ThOD Not applicable Chemical oxygen demand (COD) Not applicable Disordemical oxygen demand (COD) Not applicable Not applicable Disordemical oxygen demand (COD) Not applicable Not applicable ThOD Not applicable Disordemical oxygen demand (COD) Not applicable Not applicable ThOD Not applicable Not applicable Trinacubed 85 (Mixture) Disordemical oxygen demand (COD) Not applicable Turnacubed 85 (Mixture) Disordemical oxygen demand (COD) Not applicable Cristobalite (14464-46-1) Bioaccumulative potential No data available. Calcium fluoride (7789-75-5) BCF - Fish [1] O - 6.4 lkg (CECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpic Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. Quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil Cristobalite (14464-46-1)	Persistence and degradability	Not established.		
Chemical oxygen demand (COD) Not applicable BOD (% of ThOD) Not applicable BOD (% of ThOD) Not applicable BOD (% of ThOD) Not applicable Persistence and degradability Biodegradability: not applicable. Chemical oxygen demand (COD) Not applicable (inorganic) ThOD Not applicable (inorganic) InDO Not applicable (inorganic) InDO Not applicable (inorganic) InDO Not applicable. Chemical oxygen demand (COD) Not applicable. Chemical oxygen demand (COD) Not applicable InDO Not applicable Chemical oxygen demand (COD) Not applicable InDO Not applicable InDO Not applicable InDO Not app	cristobalite (14464-46-1)			
ThOD Not applicable BOD (% of ThOD) Not applicable calcium fluoride (7789-75-5) Persistence and degradability Biodegradability: not applicable. Chemical oxygen demand (COD) Not applicable (inorganic) ThOD Not applicable (inorganic) aluminium oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable. Chemical oxygen demand (COD) Not applicable ThOD Not applicable Quartz (14808-60-7) Persistence and degradability Not applicable Biochemical oxygen demand (BOD) Not applicable Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water. Experimental value) Bioaccumulative potential Low potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available.	Persistence and degradability	Mineral. Not applicable.		
BOD (% of ThOD) Not applicable calcium fluoride (7789-75-5) Persistence and degradability Biodegradability: not applicable. Chemical oxygen demand (COD) Not applicable (inorganic) ThOD Not applicable (inorganic) aluminium oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable ThOD Not applicable ThOD Not applicable Not applicable Not applicable Not applicable Persistence and degradability Not applicable. Biochemical oxygen demand (BOD) Not applicable. Biochemical oxygen demand (BOD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. Cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (DECD 365: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential No data available. Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available.	Chemical oxygen demand (COD)	Not applicable		
calcium fluoride (7789-75-5) Persistence and degradability Biodegradability: not applicable. Chemical oxygen demand (COD) Not applicable (inorganic) ThOD Not applicable (inorganic) aluminium oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable ThOD Not applicable ThOD Not applicable ThOD Not applicable Quartz (14808-60-7) Persistence and degradability Not applicable. Biochemical oxygen demand (BOD) Not applicable Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable ThOD Not applicable ThOD Not applicable 12.3. Bloaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0-6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential No data available. low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available.	ThOD	Not applicable		
Persistence and degradability Biodegradability: not applicable. Chemical oxygen demand (COD) Not applicable (inorganic) ThOD Not applicable (inorganic) aluminium oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable Not applicabl	BOD (% of ThOD)	Not applicable		
Chemical oxygen demand (COD) Not applicable (inorganic) Aluminium oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable Not applicable Not applicable Persistence and degradability Not applicable Not applicable Persistence and degradability Not applicable Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable Chemical oxygen demand (COD) Not applicable 12.3. Bioaccumulative potential Furna Cubed 85 (Mixture) Bioaccumulative potential Not established. Cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	calcium fluoride (7789-75-5)			
ThOD Not applicable (inorganic) aluminium oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable ThOD Not applicable quartz (14808-60-7) Persistence and degradability Not applicable. Biochemical oxygen demand (BOD) Not applicable. Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential Furna Cubed 85 (Mixture) Bioaccumulative potential Not established. Cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] O - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpior Fresh water, Experimental value) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available.	Persistence and degradability	Biodegradability: not applicable.		
aluminium oxide, non-fibrous (1344-28-1) Persistence and degradability Not applicable. Chemical oxygen demand (COD) Not applicable ThOD Not applicable quartz (14808-60-7) Persistence and degradability Not applicable. Biochemical oxygen demand (BOD) Not applicable. Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 lkg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpior Fresh water, Experimental value) Bioaccumulative potential Low potential (Dow potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available.	Chemical oxygen demand (COD)	Not applicable (inorganic)		
Persistence and degradability Chemical oxygen demand (COD) Not applicable ThOD Not applicable quartz (14808-60-7) Persistence and degradability Not applicable. Biochemical oxygen demand (BOD) Not applicable Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. Cristobalite (14464-46-1) Bioaccumulative potential No data available. Calcium fluoride (7789-75-5) BCF - Fish [1] O - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	ThOD	Not applicable (inorganic)		
Chemical oxygen demand (COD) Not applicable Quartz (14808-60-7) Persistence and degradability Not applicable. Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable Chemical oxygen demand (COD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. Cristobalite (14464-46-1) Bioaccumulative potential Not data available. Calcium fluoride (7789-75-5) BCF - Fish [1] O - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	aluminium oxide, non-fibrous (1344-28-1)			
ThOD Not applicable quartz (14808-60-7) Persistence and degradability Not applicable. Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	Persistence and degradability	Not applicable.		
quartz (14808-60-7) Persistence and degradability Not applicable. Biochemical oxygen demand (BOD) Not applicable Chemical oxygen demand (COD) Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. Cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpion Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	Chemical oxygen demand (COD)	Not applicable		
Persistence and degradability Biochemical oxygen demand (BOD) Chemical oxygen demand (COD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. Cristobalite (14464-46-1) Bioaccumulative potential No data available. Calcium fluoride (7789-75-5) BCF - Fish [1] O - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	ThOD	Not applicable		
Biochemical oxygen demand (BOD) Chemical oxygen demand (COD) Not applicable ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. Cristobalite (14464-46-1) Bioaccumulative potential No data available. Calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	quartz (14808-60-7)			
Chemical oxygen demand (COD) Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	Persistence and degradability	Not applicable.		
ThOD Not applicable 12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	Biochemical oxygen demand (BOD)	Not applicable		
12.3. Bioaccumulative potential FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	Chemical oxygen demand (COD)	Not applicable		
FurnaCubed 85 (Mixture) Bioaccumulative potential Not established. cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	ThOD	Not applicable		
Bioaccumulative potential Cristobalite (14464-46-1) Bioaccumulative potential No data available. Calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpion Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	12.3. Bioaccumulative potential			
cristobalite (14464-46-1) Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	FurnaCubed 85 (Mixture)			
Bioaccumulative potential No data available. calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	Bioaccumulative potential	Not established.		
calcium fluoride (7789-75-5) BCF - Fish [1] 0 - 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	cristobalite (14464-46-1)			
BCF - Fish [1] 0 – 6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	Bioaccumulative potential	No data available.		
Fresh water, Experimental value) Bioaccumulative potential Low potential for bioaccumulation (BCF < 500). aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	calcium fluoride (7789-75-5)			
aluminium oxide, non-fibrous (1344-28-1) Bioaccumulative potential No data available. quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil cristobalite (14464-46-1)	BCF - Fish [1]	0-6.4 l/kg (OECD 305: Bioconcentration: Flow-Through Fish Test, 4 week(s), Cyprinus carpio, Fresh water, Experimental value)		
Bioaccumulative potential Quartz (14808-60-7) Bioaccumulative potential No data available. 12.4. Mobility in soil Cristobalite (14464-46-1)	Bioaccumulative potential	Low potential for bioaccumulation (BCF < 500).		
quartz (14808-60-7) Bioaccumulative potential 12.4. Mobility in soil cristobalite (14464-46-1)	aluminium oxide, non-fibrous (1344-28-1)			
Bioaccumulative potential 12.4. Mobility in soil cristobalite (14464-46-1)	Bioaccumulative potential	No data available.		
12.4. Mobility in soil cristobalite (14464-46-1)	quartz (14808-60-7)			
cristobalite (14464-46-1)	Bioaccumulative potential	No data available.		
	12.4. Mobility in soil			
	cristobalite (14464-46-1)			
Ecology - soil No data available.	Ecology - soil	No data available.		

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

calcium fluoride (7789-75-5)		
Surface tension	No data available in the literature	
Ecology - soil No (test) data on mobility of the substance available.		
aluminium oxide, non-fibrous (1344-28-1)		
Surface tension	No data available in the literature	
Ecology - soil	No data available.	
10 T 01		

12.5. Other adverse effects

Effect on the global warming : None known

Other information : No other effects known.

SECTION 13: Disposal considerations

13.1. Disposal methods

Product/Packaging disposal recommendations : Dispose in a safe manner in accordance with local/national regulations.

Ecology - waste materials : Avoid release to the environment.

SECTION 14: Transport information

In accordance with DOT / TDG / IMDG / IATA

Department of Transportation (DOT)

In accordance with DOT

Not regulated

Transportation of Dangerous Goods

Not regulated

Transport by sea

Not regulated

Air transport

Not regulated

SECTION 15: Regulatory information

15.1. US Federal regulations

All components of this product are present and listed as Active on the United States Environmental Protection Agency Toxic Substances Control Act (TSCA) inventory

aluminium oxide, non-fibrous (1344-28-1)

Not subject to reporting requirements of the United States SARA Section 313

Note: The section 313 chemical list contains "CAS # 1344-28-1 Aluminum Oxide (Fibrous forms)"; the Aluminum oxide contained in this product is non-fibrous, and thus is not a section 313 material. Only manufacturing, processing, or otherwise use of aluminum oxide in the fibrous form triggers reporting.

15.2. International regulations

CANADA

Calcium Aluminate Cement (65997-16-2)

Listed on the Canadian DSL (Domestic Substances List)

cristobalite (14464-46-1)

Listed on the Canadian DSL (Domestic Substances List)

calcium fluoride (7789-75-5)

Listed on the Canadian DSL (Domestic Substances List)

aluminium oxide, non-fibrous (1344-28-1)

Listed on the Canadian DSL (Domestic Substances List)

EU-Regulations

No additional information available

National regulations

quartz (14808-60-7)

Listed on IARC (International Agency for Research on Cancer)

15.3. US State regulations

FurnaCubed 85 (Mixture)

U.S. - California - Proposition 65 - Other information

This product contains crystalline silica, a chemical known to the state of California to cause cancer. For more information go to WWW.P65Warnings.ca.gov

4/14/2023 (Revision date) EN (English US) 7/8

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

cristobalite (14464-46-	1)				
U.S California -	U.S California -	U.S California -	U.S California -	No significant risk	Maximum allowable
Proposition 65 -	Proposition 65 -	Proposition 65 -	Proposition 65 -	level (NSRL)	dose level (MADL)
Carcinogens List	Developmental Toxicity	Reproductive Toxicity	Reproductive Toxicity	i i	, , ,
		- Female	- Male		
Yes	No	No	No		

quartz (14808-60-7)					
U.S California -	U.S California -	U.S California -	U.S California -	No significant risk	Maximum allowable
Proposition 65 -	Proposition 65 -	Proposition 65 -	Proposition 65 -	level (NSRL)	dose level (MADL)
Carcinogens List	Developmental Toxicity	Reproductive Toxicity	Reproductive Toxicity	` '	` ´
	,	- Female	- Male		
Yes	No	No	No		

State or local regulations
U.S Massachusetts - Right To Know List; U.S New Jersey - Right to Know Hazardous
Substance List; U.S Pennsylvania - RTK (Right to Know) List
U.S Massachusetts - Right To Know List; U.S New Jersey - Right to Know Hazardous
Substance List; U.S Pennsylvania - RTK (Right to Know) List
U.S New Jersey - Right to Know Hazardous Substance List

SECTION 16: Other information

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

Revision date : 4/14/2023

Other information : Report language name. English. In the event of any conflict between English and other language

versions, the English version shall prevail.

Full text of H-phrases	
H315	Causes skin irritation
H320	Causes eye irritation
H350	May cause cancer

Safety Data Sheet (SDS), USA

This information and recommendations set forth herein are taken from sources believed to be accurate as of the date herein, however, Resco Products, Inc. makes no warranty with respect to the accuracy of the information or the suitability of the recommendations, and assumes no liability to any user thereof.

4/14/2023 (Revision date) EN (English US) 8/8